



RINSEABLE PRIMER

PRODUCT DESCRIPTION

The Rinseable Primer™ is a bio-degradable surface cleaner and degreaser. It can be used to clean various types of roofing substrates. The cleaner removes heavy accumulation of hard-to-remove dirt, oil and grease without the use of solvents. When old surfaces are cleaned properly, it will eliminate the need for solvent wiping, sanding, and grit sweeping the substrate. This will not damage grass or vegetation near the building.

- Promotes adhesion as it cleans
- Powerful degreaser
- Solvent free
- Biodegradable
- Easy to apply, low odor
- May eliminate costly abrasive sweeping
- Contains no phosphates, halogens or alkali hydroxides
- Formulated without lead or mercury containing materials
- Dramatically improves recoatability of aged, painted surfaces

RECOMMENDED USES

Recommended for cleaning roofing substrates such as:

- EPDM
- TPO
- PVC
- GALVANIZED METAL
- CONCRETE
- PREVIOUSLY PAINTED SURFACES
- **Not recommended for cleaning: Asphalt based surfaces**

Rinseable Primer™ is ideal for cleaning intact painted surfaces in preparation for repainting. It is also useful in cleaning rusted steel, galvanized metal, and masonry surfaces. It is particularly useful for cleaning dirty, greasy concrete floors, walls, machinery, and equipment in industrial and commercial environments.

SURFACE PREPARATION

All surfaces to receive the FAR® System must be power washed to remove dirt, loose rust, loose paint, chalk, and other debris which could prevent adhesion. Surface must be dry prior to coating.

APPLICATION CONDITIONS

Do not apply when rain is forecast or when temperatures are below 40°F (5°C).

APPLICATION TEMPERATURE: 40° F to 105° F (5° C to 35° C)

KEEP FROM FREEZING

PACKAGING INFORMATION

Container: 5 gallons (18.9 L)

Shipping Weight: 50.1 lbs.

Shelf Life: 24 months minimum at 77°F (25°C). Subject to re-inspection thereafter.



RINSEABLE PRIMER

APPLICATION PROCEDURES

Test clean a small area to ensure compatibility with the substrate. If surface is hot, wet before applying Rinseable Primer™. It is recommended that this be applied with low hand pump pressure sprayer. Allow cleaner to remain for five to ten minutes, but do not allow the surface to dry. Rinse with a minimum 1500 psi power washer. All of the residue must be removed so a thorough rinsing is very important. If surface is extremely dirty, moderate scrubbing will aid in performance and speed of cleaning. When completely removed, the surface will no longer foam when rinsed. Rinseable Primer™ must not be allowed to dry on the surface. Do not apply under freezing conditions. Allow the surface to dry thoroughly before applying any FAR System® products.

Adequate protective equipment and clothing such as rubber gloves and protective eyewear are recommended.

Do not apply to glass surfaces, metallic automobile finishes, aluminum surfaces which will remain unpainted or strong alkali sensitive painted surfaces. May dull glossy surfaces.

WARRANTY

Seller and manufacturers only obligation shall be to replace such quantity of product proved to be defective. Neither seller or manufacturer shall be liable for any injury, loss or damage, direct or consequential arising from the use or the inability to use the product for his/her intended use, and user assumes all risk and liability.

DISCLAIMER

The information and recommendations set forth in this product data sheet are based upon tests conducted by or on behalf of Fluid Applied Roofing, LLC. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of the publication. Consult your Fluid Applied Roofing representative to obtain the most current Product Data information.

COVERAGE RATES

Apply Rinseable Primer™ at .25 gals per square (400 sf/gal). Ensure that the entire surface is wet.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS) which Fluid Applied Roofing, has provided to its customers. All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations. In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation. If in doubt regarding the suitability of use of this product, consult Fluid Applied Roofing, for further advice.

STORAGE

Shelf Life - 24 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.