

# **RUST PRIMER**

### **PRODUCT DESCRIPTION**

Rust Primer<sup>™</sup> represents the latest technology in corrosion-resistant and rust-converting primers. This high quality, water-based, rust inhibiting, low VOC primer uses a self-cross-linking technology that provides low VOC levels with greater corrosion resistance and adhesion properties. Dries quickly to allow a faster return to service and can be top coated with any FAR<sup>®</sup> System products.

# **RECOMMENDED USES**

Over rusty metal surfaces.

### SURFACE PREPARATION

All surfaces to receive the FAR<sup>®</sup> System must be power washed to remove dirt, loose rust, loose paint, chalk, and other debris which could prevent adhesion. The surface must be dry prior to coating.

#### **APPLICATION CONDITIONS**

Application during periods of low temperature or high humidity will extend dry time. Maximum humidity 85%. Do not apply when rain is forecast or when temperatures are below 50°F (10°C). Allow 4-6 hours for the coating to dry prior to being subjected to rain, heavy dew, or temperatures below 40°F.

APPLICATION TEMPERATURE: 50° F to 105° F (10° C to 40° C) TIME BETWEEN EACH APPLICATION: 2-3 hours KEEP FROM FREEZING

# PACKAGING INFORMATION

5 gallons (18.9 L) 55 gallons (208.1 L)

# EQUIPMENT RECOMMENDATIONS

SPRAY EQUIPMENT: Graco GH 833 or equivalent.

TIP SIZES: PBR or Standing Seam Metal Roofs: Graco RAC X 625.

# APPLICATION PROCEDURES

Surface preparation must be completed as indicated in the system specifications. A field adhesion test is required before installing Fluid Applied Roofing products. Rinseable Primer Concentrate<sup>™</sup> must be used to prepare all substrates before installing any FAR System<sup>™</sup> products.

MIXING INSTRUCTIONS Mixing is required.



# **RUST PRIMER**

# **PHYSICAL PROPERTIES**

This product complies with the requirements of ASTM D 6083.

PRODUCT CHARACTERISTICS	VALUE	TEST METHOD
Color	RED	
Vehicle Base	Acrylic	
Weight per gallon	10.0 lbs. ± 0.2	
Solids	41 ± 3%	ASTM D-1644
Viscosity @ 77° F	800 ± 200 cP	ASTM D-562
VOC content	65 g/l	EPA-24
Adhesion excellent to	Galvanized Steel, Aluminum	ASTM C-794
Flash Point	None	
Solvent	Water	
Clean Up	Warm soapy water	

# WARRANTY

This product is manufactured in accordance with ISO 9001-2008 standards. Seller and manufacturers' only obligation shall be to replace such quantity of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury, loss, or damage, direct or consequential arising from the use or the inability to use the product for his/her intended use, and the user assumes all risk and liability. Color fade is not covered under warranty.

# DISCLAIMER

The information and recommendations set forth in this product datasheet are based upon tests conducted by or on behalf of Fluid Applied Roofing, LLC. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of the publication. Consult your Fluid Applied Roofing representative to obtain the most current Product Data information.

# **COVERAGE RATES**

200 square feet per gallon

# **DRY TIME**

Exposure to rain or heavy dew: 2-4 hours @ 70° F Between applications: 2-3 hours @ 70° F Before foot traffic: 2-3 hours minimum Drying time is temperature, humidity, and film thickness dependent.

# **CLEAN UP**

Remove the spray tip and spray tip guard and clean the spray equipment and accessories with water until the water is clear. Fluid Applied Roofing, LLC, including its employees, affiliates, and owners, is not liable for any injury, loss, or damage, direct or consequential, arising from cleaning solution. The user assumes all risk and liability. Once the spray equipment is clean, follow the equipment manufacturers' recommendations for storage instructions.